

### **ABSTRACT OF THE DISCLOSURE**

Flexible article having sense of touch and method of manufacturing same is disclosed. The article comprises a hollow member formed by injection molding of TPR, and a jellylike substance filled in the hollow member, the jellylike substance being formed from PVA solution. Preferably, the PVA solution is comprised of 3 wt% to 30 wt% PVA, 20 wt% to 85 wt% water, 0.5 wt% to 10 wt% plasticizer, and 0 wt% to 20 wt% softness enhancing additive.